

 **DONIT**
Made in EU

 **DONIT**
A perfect fit

TESNIT®

DONIFLEX®

GRAFILIT®

DONIFLON®

MICALIT®

WE ARE
A TRUE
PARTNER
FOR YOUR
SUCCESS

DONIT Tesnit® Sealing technologies

As a leader in gaskets, gasket sheets, and advanced sealing technologies, DONIT Tesnit® offers the optimum solution with a perfect fit for your most challenging sealing requirements. Backed by decades of excellence in understanding of sealing problems, extensive know how in application engineering, and consistent manufacturing of reliable high quality products, we are in position to respond quickly and efficiently to your inquiry.

WE ARE A TRUE PARTNER FOR YOUR SUCCESS

With a wide experience in problem-solving and unshaken commitment to high quality standards, we are dedicated to provide you the best service and products. In addition, through customer-driven innovation, our strong R&D team is qualified to successfully design the adequate sealing solution.

Our customer satisfaction rests upon four pillars:

- Complete production chain and international sales network
- Quality assurance and safety
- Application engineering
- Technical training courses and seminars

THE DONIT PHILOSOPHY

Our philosophy is based building long-term business relationship with our customers that extends across many sectors of industries. Customer satisfaction is our driving-force which is attained through the constant supply of reliable and high quality products embracing product improvement and support.

DONIT gasket support sheets and sealing solutions are high quality products which have received several industrial quality approvals. Our products support the environmental legislation without compromising their sealing performance.

EMPLOYEES

Over 200 employees dedicated to you:

We strive for permanent professional and personal growth. We promote teamwork and diversity.

Our international team supports you regardless your geographical location.

80% - Secondary school / technical school or lower

18% - Bachelor or equivalent

2% - Doctoral or equivalent

CERTIFIED QUALITY



We assure high quality, environmentally friendly products to our customers. Quality and care for the environment is embedded in both our minds and our organization.

Care for the environment is embedded in our tradition. DONIT Tesnit® is certified by international ISO 9001 and ISO 14001 standards.



We also ensure that product quality and safety is in accordance with a number of widely recognized international standards such as:


DVGW (DIN 3535-6, VP 401), SVGW (DIN 3535-6), DVGW KTW, DVGW W270, BAM, WRAS, TA-Luft (VDI 2440), API 6FA / API 607, ABS, Germanischer Lloyd





DONIFLEX® G-LD is an advanced composite material based on graphite and aramid manufactured under organic solvent-free conditions. DONIFLEX® G-LD combines the advantages of the chemical and thermal resistance of graphite with the strength of aramid. This "low density" material has high compressibility, good stress resistance and is highly flexible in adapting to uneven flanges. It has wide application range in particular for steam supply, chemicals, and heating systems.

PROPERTIES



APPROPRIATE INDUSTRIES & APPLICATIONS

- GENERAL PURPOSE
- WATER SUPPLY
- POTABLE WATER SUPPLY
- STEAM SUPPLY
- CHEMICAL INDUSTRY
- PETROCHEMICAL INDUSTRY
- PAPER AND CELLULOSE INDUSTRY
- AUTOMOTIVE AND ENGINE BUILDING INDUSTRY
- POWER PLANT
- HEATING SYSTEMS
- HIGH TEMP. APPLICATIONS
- VALVES


Composition	Aramid fibres, natural graphite, inorganic fillers, NBR binder.
Colour	Grey
Approvals	WRAS, TA-Luft (VDI 2440), DVGW W270

TECHNICAL DATA Typical values for a thickness of 2 mm

Density	DIN 28090-2	g/cm ³	1.2
Compressibility	ASTM F36J	%	35
Recovery	ASTM F36J	%	17
Tensile strength	ASTM F152	MPa	4.5
Stress resistance	DIN 52913		
50 MPa, 16 h, 175 °C		MPa	40
50 MPa, 16 h, 300 °C		MPa	35
Specific leak rate	DIN 3535-6	mg/(s·m)	0.5
Thickness increase	ASTM F146		
Oil IRM 903, 5 h, 150 °C		%	3
ASTM Fuel B, 5 h, 23 °C		%	2
Weight increase			
Oil IRM 903, 5 h, 150 °C		%	30
ASTM Fuel B, 5 h, 23 °C		%	25
Compression modulus	DIN 28090-2		
At room temperature: ϵ_{KSW}		%	26
At elevated temperature: $\epsilon_{WSW/200\text{ °C}}$		%	5
Percentage creep relaxation	DIN 28090-2		
At room temperature: ϵ_{KRW}		%	3.0
At elevated temperature: $\epsilon_{WRW/200\text{ °C}}$		%	0.5
Creep deformation			
Change in thickness at 20 °C, 50 MPa		%	33
Change in thickness at 300 °C, 50 MPa		%	8
Change in thickness at 400 °C, 50 MPa		%	17

P-T DIAGRAM

EN 1514-1, Type IBC, PN 40, DIN 28091-2 / 3.8, 2.0 mm



- General suitability - Under common installation practices and chemical compatibility.
- Conditional suitability - Appropriate measures ensure maximum performance for joint design and gasket installation. Technical consultation is recommended.
- Limited suitability - Technical consultation is mandatory.

Dimensions of standard sheets

Sheet size (mm): 1500 x 1480 | 2000 x 1480

Thickness (mm): 0.5 | 1.0 | 1.5 | 2.0 | 3.0

Other dimensions and thicknesses are available on request.

Acetamide	+	Dioxane	?	Oleic acid	+
Acetic acid, 10%	+	Diphytl (Dowtherm A)	+	Oleum (Sulfuric acid, fuming)	-
Acetic acid, 100% (Glacial)	?	Esters	?	Oxalic acid	+
Acetone	?	Ethane (gas)	+	Oxygen (gas)	+
Acetonitrile	-	Ethers	?	Palmitic acid	+
Acetylene (gas)	+	Ethyl acetate	?	Paraffin oil	+
Acid chlorides	-	Ethyl alcohol (Ethanol)	+	Pentane	+
Acrylic acid	+	Ethyl cellulose	?	Perchloroethylene	?
Acrylonitrile	-	Ethyl chloride (gas)	?	Petroleum (Crude oil)	+
Adipic acid	+	Ethylene (gas)	+	Phenol (Carbolic acid)	-
Air (gas)	+	Ethylene glycol	+	Phosphoric acid, 40%	?
Alcohols	+	Formaldehyde (Formalin)	?	Phosphoric acid, 85%	?
Aldehydes	?	Formamide	+	Phthalic acid	+
Alum	+	Formic acid, 10%	+	Potassium acetate	+
Aluminium acetate	+	Formic acid, 85%	?	Potassium bicarbonate	+
Aluminium chlorate	+	Formic acid, 100%	?	Potassium carbonate	+
Aluminium chloride	+	Freon-12 [R-12]	+	Potassium chloride	+
Aluminium sulfate	+	Freon-134a [R-134a]	+	Potassium cyanide	+
Amines	-	Freon-22 [R-22]	?	Potassium dichromate	?
Ammonia (gas)	?	Fruit juices	+	Potassium hydroxide	?
Ammonium bicarbonate	+	Fuel oil	+	Potassium iodide	+
Ammonium chloride	+	Gasoline	+	Potassium nitrate	+
Ammonium hydroxide	?	Gelatin	+	Potassium permanganate	?
Amyl acetate	?	Glycerine (Glycerol)	+	Propane (gas)	+
Anhydrides	?	Glycols	+	Propylene (gas)	+
Aniline	-	Helium (gas)	+	Pyridine	-
Anisole	+	Heptane	+	Salicylic acid	?
Argon (gas)	+	Hydraulic oil (Glycol based)	+	Seawater/brine	+
Asphalt	+	Hydraulic oil (Mineral type)	+	Silicones (oil/grease)	+
Barium chloride	+	Hydraulic oil (Phosphate ester based)	+	Soaps	+
Benzaldehyde	?	Hydrazine	-	Sodium aluminate	+
Benzene	+	Hydrocarbons	+	Sodium bicarbonate	+
Benzoic acid	+	Hydrochloric acid, 10%	?	Sodium bisulfite	+
Bio-diesel	+	Hydrochloric acid, 37%	-	Sodium carbonate	+
Bio-ethanol	+	Hydrofluoric acid, 10%	-	Sodium chloride	+
Black liquor	+	Hydrofluoric acid, 48%	-	Sodium cyanide	+
Borax	+	Hydrogen (gas)	+	Sodium hydroxide	?
Boric acid	+	Iron sulfate	+	Sodium hypochlorite (Bleach)	?
Butadiene (gas)	+	Isobutane (gas)	+	Sodium silicate (Water glass)	+
Butane (gas)	+	Isooctane	+	Sodium sulfate	+
Butyl alcohol (Butanol)	+	Isoprene	+	Sodium sulfide	+
Butyric acid	+	Isopropyl alcohol (Isopropanol)	+	Starch	+
Calcium chloride	+	Kerosene	+	Steam	+
Calcium hydroxide	+	Ketones	?	Stearic acid	+
Carbon dioxide (gas)	+	Lactic acid	+	Styrene	?
Carbon monoxide (gas)	+	Lead acetate	+	Sugars	+
Cellosolve	?	Lead arsenate	+	Sulfur	?
Chlorine (gas)	?	Magnesium sulfate	+	Sulfur dioxide (gas)	?
Chlorine (in water)	?	Maleic acid	+	Sulfuric acid, 20%	-
Chlorobenzene	?	Malic acid	+	Sulfuric acid, 98%	-
Chloroform	?	Methane (gas)	+	Sulfuryl chloride	-
Chloroprene	?	Methyl alcohol (Methanol)	+	Tar	+
Chlorosilanes	-	Methyl chloride (gas)	?	Tartaric acid	+
Chromic acid	-	Methylene dichloride	?	Tetrahydrofuran (THF)	?
Citric acid	+	Methyl ethyl ketone (MEK)	?	Titanium tetrachloride	+
Copper acetate	+	N-Methyl-pyrrolidone (NMP)	?	Toluene	+
Copper sulfate	+	Milk	+	2,4-Toluenediisocyanate	?
Creosote	?	Mineral oil (ASTM no.1)	+	Transformer oil (Mineral type)	+
Cresols (Cresylic acid)	?	Motor oil	+	Trichloroethylene	?
Cyclohexane	+	Naphtha	+	Vinegar	+
Cyclohexanol	+	Nitric acid, 10%	?	Vinyl chloride (gas)	?
Cyclohexanone	?	Nitric acid, 65%	-	Vinylidene chloride	?
Decalin	+	Nitrobenzene	?	Water	+
Dextrin	+	Nitrogen (gas)	+	White spirits	+
Dibenzyl ether	?	Nitrous gases (NOx)	?	Xylenes	+
Dibutyl phthalate	?	Octane	+	Xylenol	-
Dimethylacetamide (DMA)	?	Oils (Essential)	+	Zinc sulfate	+
Dimethylformamide (DMF)	?	Oils (Vegetable)	+		

CHEMICAL RESISTANCE CHART

The recommendations made here are intended to be a guideline for the selection of the suitable gasket quality. Because the function and durability of the products depend upon a number of factors, the data may not be used to support any warranty claims.

- + Recommended
- ? Recommendation depends on operating conditions
- Not recommended



DONIT TESNIT®, d.o.o.

Cesta komandanta Staneta 38
1215 Medvode, Slovenia

Phone: +386 (0)1 582 33 00

Fax: +386 (0)1 582 32 06
+386 (0)1 582 32 08

Web: www.donit.eu

E-mail: info@donit.eu

Copyright © 2015 DONIT TESNIT, d.o.o.

All rights reserved

Date of issue: 01.06.2015 / TDS-DGLD-05-2015



DONIFLEX® G-MD is an advanced composite material based on graphite and aramid manufactured under organic solvent-free conditions. DONIFLEX® G-MD combines the advantages of the chemical and thermal resistance of graphite with the strength of aramid. This "medium density" material has good stress resistance for gaskets with narrow-width. It is particularly suitable for steam and hot water supplies as well as for boilers or radiators.

PROPERTIES

SUPERIOR				
EXCELENT		MECHANICAL RESISTANCE	THERMAL RESISTANCE	CHEMICAL RESISTANCE
VERY GOOD				
GOOD				SEALABILITY PERFORMANCE
MODERATE				

APPROPRIATE INDUSTRIES & APPLICATIONS

- GENERAL PURPOSE
- WATER SUPPLY
- STEAM SUPPLY
- PETROCHEMICAL INDUSTRY
- PAPER AND CELLULOSE INDUSTRY
- AUTOMOTIVE AND ENGINE BUILDING INDUSTRY
- SHIPBUILDING
- POWER PLANT
- HEATING SYSTEMS
- HIGH TEMP. APPLICATIONS


Composition	Aramid fibres, natural graphite, inorganic fillers, NBR binder.
Colour	Grey
Approvals	Please inquire.

TECHNICAL DATA Typical values for a thickness of 1 mm

Density	DIN 28090-2	g/cm ³	1.4
Compressibility	ASTM F36J	%	20
Recovery	ASTM F36J	%	32
Tensile strength	ASTM F152	MPa	9
Stress resistance	DIN 52913		
50 MPa, 16 h, 175 °C		MPa	45
50 MPa, 16 h, 300 °C		MPa	40
Specific leak rate	DIN 3535-6	mg/(s·m)	0.5
Thickness increase	ASTM F146		
Oil IRM 903, 5 h, 150 °C		%	5
ASTM Fuel B, 5 h, 23 °C		%	5
Weight increase			
Oil IRM 903, 5 h, 150 °C		%	20
ASTM Fuel B, 5 h, 23 °C		%	17
Compression modulus	DIN 28090-2		
At room temperature: ϵ_{KSW}		%	17
At elevated temperature: $\epsilon_{WSW/200\text{ °C}}$		%	5
Percentage creep relaxation	DIN 28090-2		
At room temperature: ϵ_{KRW}		%	2.6
At elevated temperature: $\epsilon_{WRW/200\text{ °C}}$		%	0.2
Creep deformation			
Change in thickness at 20 °C, 50 MPa		%	18
Change in thickness at 300 °C, 50 MPa		%	10
Change in thickness at 400 °C, 50 MPa		%	15

P-T DIAGRAM

EN 1514-1, Type IBC, PN 40, DIN 28091-2 / 3.8, 2.0 mm



- General suitability - Under common installation practices and chemical compatibility.
- Conditional suitability - Appropriate measures ensure maximum performance for joint design and gasket installation. Technical consultation is recommended.
- Limited suitability - Technical consultation is mandatory.

Dimensions of standard sheets

Sheet size (mm): 1500 x 1480 | 2000 x 1480

Thickness (mm): 0.5 | 1.0 | 1.5 | 2.0 | 3.0

Other dimensions and thicknesses are available on request.

Acetamide	+	Dioxane	?	Oleic acid	+
Acetic acid, 10%	+	Diphytl (Dowtherm A)	+	Oleum (Sulfuric acid, fuming)	-
Acetic acid, 100% (Glacial)	?	Esters	?	Oxalic acid	+
Acetone	?	Ethane (gas)	+	Oxygen (gas)	+
Acetonitrile	-	Ethers	?	Palmitic acid	+
Acetylene (gas)	+	Ethyl acetate	?	Paraffin oil	+
Acid chlorides	-	Ethyl alcohol (Ethanol)	+	Pentane	+
Acrylic acid	+	Ethyl cellulose	?	Perchloroethylene	?
Acrylonitrile	-	Ethyl chloride (gas)	?	Petroleum (Crude oil)	+
Adipic acid	+	Ethylene (gas)	+	Phenol (Carbolic acid)	-
Air (gas)	+	Ethylene glycol	+	Phosphoric acid, 40%	?
Alcohols	+	Formaldehyde (Formalin)	?	Phosphoric acid, 85%	?
Aldehydes	?	Formamide	+	Phthalic acid	+
Alum	+	Formic acid, 10%	+	Potassium acetate	+
Aluminium acetate	+	Formic acid, 85%	?	Potassium bicarbonate	+
Aluminium chlorate	+	Formic acid, 100%	?	Potassium carbonate	+
Aluminium chloride	+	Freon-12 [R-12]	+	Potassium chloride	+
Aluminium sulfate	+	Freon-134a [R-134a]	+	Potassium cyanide	+
Amines	-	Freon-22 [R-22]	?	Potassium dichromate	?
Ammonia (gas)	?	Fruit juices	+	Potassium hydroxide	?
Ammonium bicarbonate	+	Fuel oil	+	Potassium iodide	+
Ammonium chloride	+	Gasoline	+	Potassium nitrate	+
Ammonium hydroxide	?	Gelatin	+	Potassium permanganate	?
Amyl acetate	?	Glycerine (Glycerol)	+	Propane (gas)	+
Anhydrides	?	Glycols	+	Propylene (gas)	+
Aniline	-	Helium (gas)	+	Pyridine	-
Anisole	+	Heptane	+	Salicylic acid	?
Argon (gas)	+	Hydraulic oil (Glycol based)	+	Seawater/brine	+
Asphalt	+	Hydraulic oil (Mineral type)	+	Silicones (oil/grease)	+
Barium chloride	+	Hydraulic oil (Phosphate ester based)	+	Soaps	+
Benzaldehyde	?	Hydrazine	-	Sodium aluminate	+
Benzene	+	Hydrocarbons	+	Sodium bicarbonate	+
Benzoic acid	+	Hydrochloric acid, 10%	?	Sodium bisulfite	+
Bio-diesel	+	Hydrochloric acid, 37%	-	Sodium carbonate	+
Bio-ethanol	+	Hydrofluoric acid, 10%	-	Sodium chloride	+
Black liquor	+	Hydrofluoric acid, 48%	-	Sodium cyanide	+
Borax	+	Hydrogen (gas)	+	Sodium hydroxide	?
Boric acid	+	Iron sulfate	+	Sodium hypochlorite (Bleach)	?
Butadiene (gas)	+	Isobutane (gas)	+	Sodium silicate (Water glass)	+
Butane (gas)	+	Isooctane	+	Sodium sulfate	+
Butyl alcohol (Butanol)	+	Isoprene	+	Sodium sulfide	+
Butyric acid	+	Isopropyl alcohol (Isopropanol)	+	Starch	+
Calcium chloride	+	Kerosene	+	Steam	+
Calcium hydroxide	+	Ketones	?	Stearic acid	+
Carbon dioxide (gas)	+	Lactic acid	+	Styrene	?
Carbon monoxide (gas)	+	Lead acetate	+	Sugars	+
Cellosolve	?	Lead arsenate	+	Sulfur	?
Chlorine (gas)	?	Magnesium sulfate	+	Sulfur dioxide (gas)	?
Chlorine (in water)	?	Maleic acid	+	Sulfuric acid, 20%	-
Chlorobenzene	?	Malic acid	+	Sulfuric acid, 98%	-
Chloroform	?	Methane (gas)	+	Sulfuryl chloride	-
Chloroprene	?	Methyl alcohol (Methanol)	+	Tar	+
Chlorosilanes	-	Methyl chloride (gas)	?	Tartaric acid	+
Chromic acid	-	Methylene dichloride	?	Tetrahydrofuran (THF)	?
Citric acid	+	Methyl ethyl ketone (MEK)	?	Titanium tetrachloride	+
Copper acetate	+	N-Methyl-pyrrolidone (NMP)	?	Toluene	+
Copper sulfate	+	Milk	+	2,4-Toluenediisocyanate	?
Creosote	?	Mineral oil (ASTM no.1)	+	Transformer oil (Mineral type)	+
Cresols (Cresylic acid)	?	Motor oil	+	Trichloroethylene	?
Cyclohexane	+	Naphtha	+	Vinegar	+
Cyclohexanol	+	Nitric acid, 10%	?	Vinyl chloride (gas)	?
Cyclohexanone	?	Nitric acid, 65%	-	Vinylidene chloride	?
Decalin	+	Nitrobenzene	?	Water	+
Dextrin	+	Nitrogen (gas)	+	White spirits	+
Dibenzyl ether	?	Nitrous gases (NOx)	?	Xylenes	+
Dibutyl phthalate	?	Octane	+	Xylenol	-
Dimethylacetamide (DMA)	?	Oils (Essential)	+	Zinc sulfate	+
Dimethylformamide (DMF)	?	Oils (Vegetable)	+		

CHEMICAL RESISTANCE CHART

The recommendations made here are intended to be a guideline for the selection of the suitable gasket quality. Because the function and durability of the products depend upon a number of factors, the data may not be used to support any warranty claims.

- + Recommended
- ? Recommendation depends on operating conditions
- Not recommended



DONIT TESNIT®, d.o.o.

Cesta komandanta Staneta 38
1215 Medvode, Slovenia

Phone: +386 (0)1 582 33 00

Fax: +386 (0)1 582 32 06
+386 (0)1 582 32 08

Web: www.donit.eu

E-mail: info@donit.eu

Copyright © 2015 DONIT TESNIT, d.o.o.

All rights reserved

Date of issue: 01.06.2015 / TDS-DGMD-05-2015













DONIFLEX® G-HD is an advanced composite material based on graphite and aramid manufactured under organic solvent-free conditions. DONIFLEX® G-HD combines the advantages of the chemical and thermal resistance of graphite with the strength of aramid. This "high density" material has very good stress resistance and sealability at elevated temperatures under continuous load. It is ideal in particular for petrochemicals and power plants.

PROPERTIES

SUPERIOR				
EXCELENT				
VERY GOOD				
GOOD				
MODERATE				

MECHANICAL RESISTANCE | THERMAL RESISTANCE | CHEMICAL RESISTANCE | SEALABILITY PERFORMANCE

APPROPRIATE INDUSTRIES & APPLICATIONS

-  GENERAL PURPOSE
-  STEAM SUPPLY
-  GAS SUPPLY
-  CHEMICAL INDUSTRY
-  PETROCHEMICAL INDUSTRY
-  PAPER AND CELLULOSE INDUSTRY
-  SHIPBUILDING
-  POWER PLANT
-  HEATING SYSTEMS
-  HIGH TEMP. APPLICATIONS

Composition	Aramid fibres, natural graphite, inorganic fillers, NBR binder.
Colour	Grey
Approvals	Please inquire.

TECHNICAL DATA Typical values for a thickness of 1.5 mm

Density	DIN 28090-2	g/cm ³	1.5
Compressibility	ASTM F36J	%	15
Recovery	ASTM F36J	%	45
Tensile strength	ASTM F152	MPa	8
Stress resistance	DIN 52913		
50 MPa, 16 h, 175 °C		MPa	42
50 MPa, 16 h, 300 °C		MPa	38
Specific leak rate	DIN 3535-6	mg/(s·m)	0.1
Thickness increase	ASTM F146		
Oil IRM 903, 5 h, 150 °C		%	5
ASTM Fuel B, 5 h, 23 °C		%	5
Weight increase			
Oil IRM 903, 5 h, 150 °C		%	15
ASTM Fuel B, 5 h, 23 °C		%	15
Compression modulus	DIN 28090-2		
At room temperature: ϵ_{KSW}		%	6
At elevated temperature: $\epsilon_{WSW/200\text{ °C}}$		%	6
Percentage creep relaxation	DIN 28090-2		
At room temperature: ϵ_{KRW}		%	4.0
At elevated temperature: $\epsilon_{WRW/200\text{ °C}}$		%	0.5
Creep deformation			
Change in thickness at 20 °C, 50 MPa		%	15
Change in thickness at 300 °C, 50 MPa		%	7
Change in thickness at 400 °C, 50 MPa		%	/

Dimensions of standard sheets

Sheet size (mm): 1500 x 1480 | 2000 x 1480

Thickness (mm): 1.0 | 1.5 | 2.0 | 3.0

Other dimensions and thicknesses are available on request.

Acetamide	+	Dioxane	?	Oleic acid	+
Acetic acid, 10%	+	Diphytl (Dowtherm A)	+	Oleum (Sulfuric acid, fuming)	-
Acetic acid, 100% (Glacial)	?	Esters	?	Oxalic acid	+
Acetone	?	Ethane (gas)	+	Oxygen (gas)	+
Acetonitrile	-	Ethers	?	Palmitic acid	+
Acetylene (gas)	+	Ethyl acetate	?	Paraffin oil	+
Acid chlorides	-	Ethyl alcohol (Ethanol)	+	Pentane	+
Acrylic acid	+	Ethyl cellulose	?	Perchloroethylene	?
Acrylonitrile	-	Ethyl chloride (gas)	?	Petroleum (Crude oil)	+
Adipic acid	+	Ethylene (gas)	+	Phenol (Carbolic acid)	-
Air (gas)	+	Ethylene glycol	+	Phosphoric acid, 40%	?
Alcohols	+	Formaldehyde (Formalin)	?	Phosphoric acid, 85%	?
Aldehydes	?	Formamide	+	Phthalic acid	+
Alum	+	Formic acid, 10%	+	Potassium acetate	+
Aluminium acetate	+	Formic acid, 85%	?	Potassium bicarbonate	+
Aluminium chlorate	+	Formic acid, 100%	?	Potassium carbonate	+
Aluminium chloride	+	Freon-12 (R-12)	+	Potassium chloride	+
Aluminium sulfate	+	Freon-134a (R-134a)	+	Potassium cyanide	+
Amines	-	Freon-22 (R-22)	?	Potassium dichromate	?
Ammonia (gas)	?	Fruit juices	+	Potassium hydroxide	?
Ammonium bicarbonate	+	Fuel oil	+	Potassium iodide	+
Ammonium chloride	+	Gasoline	+	Potassium nitrate	+
Ammonium hydroxide	?	Gelatin	+	Potassium permanganate	?
Amyl acetate	?	Glycerine (Glycerol)	+	Propane (gas)	+
Anhydrides	?	Glycols	+	Propylene (gas)	+
Aniline	-	Helium (gas)	+	Pyridine	-
Anisole	+	Heptane	+	Salicylic acid	?
Argon (gas)	+	Hydraulic oil (Glycol based)	+	Seawater/brine	+
Asphalt	+	Hydraulic oil (Mineral type)	+	Silicones (oil/grease)	+
Barium chloride	+	Hydraulic oil (Phosphate ester based)	+	Soaps	+
Benzaldehyde	?	Hydrazine	-	Sodium aluminate	+
Benzene	+	Hydrocarbons	+	Sodium bicarbonate	+
Benzoic acid	+	Hydrochloric acid, 10%	?	Sodium bisulfite	+
Bio-diesel	+	Hydrochloric acid, 37%	-	Sodium carbonate	+
Bio-ethanol	+	Hydrofluoric acid, 10%	-	Sodium chloride	+
Black liquor	+	Hydrofluoric acid, 48%	-	Sodium cyanide	+
Borax	+	Hydrogen (gas)	+	Sodium hydroxide	?
Boric acid	+	Iron sulfate	+	Sodium hypochlorite (Bleach)	?
Butadiene (gas)	+	Isobutane (gas)	+	Sodium silicate (Water glass)	+
Butane (gas)	+	Isooctane	+	Sodium sulfate	+
Butyl alcohol (Butanol)	+	Isoprene	+	Sodium sulfide	+
Butyric acid	+	Isopropyl alcohol (Isopropanol)	+	Starch	+
Calcium chloride	+	Kerosene	+	Steam	+
Calcium hydroxide	+	Ketones	?	Stearic acid	+
Carbon dioxide (gas)	+	Lactic acid	+	Styrene	?
Carbon monoxide (gas)	+	Lead acetate	+	Sugars	+
Cellosolve	?	Lead arsenate	+	Sulfur	?
Chlorine (gas)	?	Magnesium sulfate	+	Sulfur dioxide (gas)	?
Chlorine (in water)	?	Maleic acid	+	Sulfuric acid, 20%	-
Chlorobenzene	?	Malic acid	+	Sulfuric acid, 98%	-
Chloroform	?	Methane (gas)	+	Sulfuryl chloride	-
Chloroprene	?	Methyl alcohol (Methanol)	+	Tar	+
Chlorosilanes	-	Methyl chloride (gas)	?	Tartaric acid	+
Chromic acid	-	Methylene dichloride	?	Tetrahydrofuran (THF)	?
Citric acid	+	Methyl ethyl ketone (MEK)	?	Titanium tetrachloride	+
Copper acetate	+	N-Methyl-pyrrolidone (NMP)	?	Toluene	+
Copper sulfate	+	Milk	+	2,4-Toluenediisocyanate	?
Creosote	?	Mineral oil (ASTM no.1)	+	Transformer oil (Mineral type)	+
Cresols (Cresylic acid)	?	Motor oil	+	Trichloroethylene	?
Cyclohexane	+	Naphtha	+	Vinegar	+
Cyclohexanol	+	Nitric acid, 10%	?	Vinyl chloride (gas)	?
Cyclohexanone	?	Nitric acid, 65%	-	Vinylidene chloride	?
Decalin	+	Nitrobenzene	?	Water	+
Dextrin	+	Nitrogen (gas)	+	White spirits	+
Dibenzyl ether	?	Nitrous gases (NOx)	?	Xylenes	+
Dibutyl phthalate	?	Octane	+	Xylenol	-
Dimethylacetamide (DMA)	?	Oils (Essential)	+	Zinc sulfate	+
Dimethylformamide (DMF)	?	Oils (Vegetable)	+		

CHEMICAL RESISTANCE CHART

The recommendations made here are intended to be a guideline for the selection of the suitable gasket quality. Because the function and durability of the products depend upon a number of factors, the data may not be used to support any warranty claims.

- + Recommended
- ? Recommendation depends on operating conditions
- Not recommended



DONIT TESNIT®, d.o.o.

Cesta komandanta Staneta 38
1215 Medvode, Slovenia

Phone: +386 (0)1 582 33 00

Fax: +386 (0)1 582 32 06
+386 (0)1 582 32 08

Web: www.donit.eu

E-mail: info@donit.eu

Copyright © 2015 DONIT TESNIT, d.o.o.

All rights reserved

Date of issue: 01.06.2015 / TDS-DGHD-05-2015



DONIFLEX® G-EM is an advanced composite material based on graphite and aramid manufactured under organic solvent-free conditions. DONIFLEX® G-EM is reinforced with expanded galvanized steel sheet insert. Even surface pressure distribution on gasket provides excellent thermomechanical properties and very good sealing characteristics. Therefore material is particularly suitable for petrochemicals, high temperature applications, and valves.

PROPERTIES

SUPERIOR EXCELLENT VERY GOOD GOOD MODERATE	THERMAL RESISTANCE		SEALABILITY PERFORMANCE	CHEMICAL RESISTANCE
	MECHANICAL RESISTANCE			

APPROPRIATE INDUSTRIES & APPLICATIONS

- STEAM SUPPLY
- POWER PLANT
- PETROCHEMICAL INDUSTRY
- HEATING SYSTEMS
- PAPER AND CELLULOSE INDUSTRY
- HIGH TEMP. APPLICATIONS
- AUTOMOTIVE AND ENGINE BUILDING INDUSTRY
- VALVES
- SHIPBUILDING


Composition	Aramid fibres, natural graphite, inorganic fillers, NBR binder. Expanded galvanized steel sheet insert (0.4 mm).
Colour	Grey
Approvals	Please inquire.

TECHNICAL DATA Typical values for a thickness of 2 mm

Density	DIN 28090-2	g/cm ³	1.7
Compressibility	ASTM F36J	%	20
Recovery	ASTM F36J	%	30
Tensile strength	ASTM F152	MPa	15
Stress resistance	DIN 52913		
50 MPa, 16 h, 175 °C		MPa	40
50 MPa, 16 h, 300 °C		MPa	35
Specific leak rate	DIN 3535-6	mg/(s·m)	0.1
Thickness increase	ASTM F146		
Oil IRM 903, 5 h, 150 °C		%	8
ASTM Fuel B, 5 h, 23 °C		%	8
Weight increase			
Oil IRM 903, 5 h, 150 °C		%	18
ASTM Fuel B, 5 h, 23 °C		%	18
Compression modulus	DIN 28090-2		
At room temperature: ϵ_{KSW}		%	7
At elevated temperature: $\epsilon_{WSW/200\text{ °C}}$		%	7
Percentage creep relaxation	DIN 28090-2		
At room temperature: ϵ_{KRW}		%	3.5
At elevated temperature: $\epsilon_{WRW/200\text{ °C}}$		%	0.7
Creep deformation			
Change in thickness at 20 °C, 50 MPa		%	18
Change in thickness at 300 °C, 50 MPa		%	8
Change in thickness at 400 °C, 50 MPa		%	10

P-T DIAGRAM

EN 1514-1, Type IBC, PN 40, DIN 28091-2 / 3.8, 2.0 mm



- General suitability - Under common installation practices and chemical compatibility.
- Conditional suitability - Appropriate measures ensure maximum performance for joint design and gasket installation. Technical consultation is recommended.
- Limited suitability - Technical consultation is mandatory.

Dimensions of standard sheets

Sheet size (mm): 1500 x 1480
 Thickness (mm): 1.0 | 1.5 | 2.0 | 3.0 | 4.0
 Other dimensions and thicknesses are available on request.

Acetamide	+	Dioxane	?	Oleic acid	-
Acetic acid, 10%	-	Diphytl (Dowtherm A)	+	Oleum (Sulfuric acid, fuming)	-
Acetic acid, 100% (Glacial)	-	Esters	?	Oxalic acid	-
Acetone	?	Ethane (gas)	+	Oxygen (gas)	-
Acetonitrile	-	Ethers	?	Palmitic acid	-
Acetylene (gas)	+	Ethyl acetate	?	Paraffin oil	+
Acid chlorides	-	Ethyl alcohol (Ethanol)	+	Pentane	+
Acrylic acid	-	Ethyl cellulose	?	Perchloroethylene	?
Acrylonitrile	-	Ethyl chloride (gas)	?	Petroleum (Crude oil)	+
Adipic acid	+	Ethylene (gas)	+	Phenol (Carbolic acid)	-
Air (gas)	+	Ethylene glycol	+	Phosphoric acid, 40%	-
Alcohols	+	Formaldehyde (Formalin)	?	Phosphoric acid, 85%	-
Aldehydes	?	Formamide	+	Phthalic acid	-
Alum	-	Formic acid, 10%	-	Potassium acetate	-
Aluminium acetate	-	Formic acid, 85%	-	Potassium bicarbonate	+
Aluminium chlorate	-	Formic acid, 100%	-	Potassium carbonate	+
Aluminium chloride	-	Freon-12 [R-12]	+	Potassium chloride	-
Aluminium sulfate	-	Freon-134a [R-134a]	+	Potassium cyanide	-
Amines	-	Freon-22 [R-22]	?	Potassium dichromate	-
Ammonia (gas)	?	Fruit juices	-	Potassium hydroxide	?
Ammonium bicarbonate	+	Fuel oil	+	Potassium iodide	-
Ammonium chloride	-	Gasoline	+	Potassium nitrate	-
Ammonium hydroxide	?	Gelatin	+	Potassium permanganate	-
Amyl acetate	?	Glycerine (Glycerol)	+	Propane (gas)	+
Anhydrides	-	Glycols	+	Propylene (gas)	+
Aniline	-	Helium (gas)	+	Pyridine	-
Anisole	+	Heptane	+	Salicylic acid	-
Argon (gas)	+	Hydraulic oil (Glycol based)	+	Seawater/brine	-
Asphalt	+	Hydraulic oil (Mineral type)	+	Silicones (oil/grease)	+
Barium chloride	-	Hydraulic oil (Phosphate ester based)	+	Soaps	+
Benzaldehyde	?	Hydrazine	-	Sodium aluminate	+
Benzene	+	Hydrocarbons	+	Sodium bicarbonate	+
Benzoic acid	+	Hydrochloric acid, 10%	-	Sodium bisulfite	-
Bio-diesel	+	Hydrochloric acid, 37%	-	Sodium carbonate	+
Bio-ethanol	+	Hydrofluoric acid, 10%	-	Sodium chloride	-
Black liquor		Hydrofluoric acid, 48%	-	Sodium cyanide	-
Borax	+	Hydrogen (gas)	+	Sodium hydroxide	?
Boric acid	+	Iron sulfate	+	Sodium hypochlorite (Bleach)	-
Butadiene (gas)	+	Isobutane (gas)	+	Sodium silicate (Water glass)	?
Butane (gas)	+	Isooctane	+	Sodium sulfate	+
Butyl alcohol (Butanol)	+	Isoprene	+	Sodium sulfide	-
Butyric acid	-	Isopropyl alcohol (Isopropanol)	+	Starch	+
Calcium chloride	-	Kerosene	+	Steam	-
Calcium hydroxide	+	Ketones	?	Stearic acid	-
Carbon dioxide (gas)	+	Lactic acid	-	Styrene	?
Carbon monoxide (gas)	+	Lead acetate	-	Sugars	+
Cellosolve	?	Lead arsenate	-	Sulfur	?
Chlorine (gas)	-	Magnesium sulfate	+	Sulfur dioxide (gas)	?
Chlorine (in water)	-	Maleic acid	-	Sulfuric acid, 20%	-
Chlorobenzene	?	Malic acid	-	Sulfuric acid, 98%	-
Chloroform	?	Methane (gas)	+	Sulfuryl chloride	-
Chloroprene	?	Methyl alcohol (Methanol)	+	Tar	+
Chlorosilanes	?	Methyl chloride (gas)	?	Tartaric acid	-
Chromic acid	-	Methylene dichloride	?	Tetrahydrofuran (THF)	?
Citric acid	-	Methyl ethyl ketone (MEK)	?	Titanium tetrachloride	-
Copper acetate	-	N-Methyl-pyrrolidone (NMP)	?	Toluene	-
Copper sulfate	-	Milk	+	2,4-Toluenediisocyanate	?
Creosote	?	Mineral oil (ASTM no.1)	+	Transformer oil (Mineral type)	-
Cresols (Cresylic acid)	?	Motor oil	+	Trichloroethylene	?
Cyclohexane	+	Naphtha	+	Vinegar	-
Cyclohexanol	+	Nitric acid, 10%	-	Vinyl chloride (gas)	?
Cyclohexanone	?	Nitric acid, 65%	-	Vinylidene chloride	?
Decalin	+	Nitrobenzene	?	Water	-
Dextrin	+	Nitrogen (gas)	+	White spirits	+
Dibenzyl ether	?	Nitrous gases (NOx)	-	Xylenes	+
Dibutyl phthalate	?	Octane	+	Xylenol	-
Dimethylacetamide (DMA)	?	Oils (Essential)	+	Zinc sulfate	-
Dimethylformamide (DMF)	?	Oils (Vegetable)	+		

CHEMICAL RESISTANCE CHART

The recommendations made here are intended to be a guideline for the selection of the suitable gasket quality. Because the function and durability of the products depend upon a number of factors, the data may not be used to support any warranty claims.

- + Recommended
- ? Recommendation depends on operating conditions
- Not recommended



DONIT TESNIT®, d.o.o.

Cesta komandanta Staneta 38
 1215 Medvode, Slovenia

Phone: +386 (0)1 582 33 00

Fax: +386 (0)1 582 32 06
 +386 (0)1 582 32 08

Web: www.donit.eu

E-mail: info@donit.eu

Copyright © 2015 DONIT TESNIT, d.o.o.

All rights reserved

Date of issue: 01.06.2015 / TDS-DGEM-05-2015



A perfect fit
of **TRUST**
COMMITMENT
POSSIBILITIES

Customer and challenge
driven innovation

High level of flexibility

Adapt to new changes

Broad portfolio of gasket materials and products

BEST PRACTICE
SOLUTIONS

Slovenia**DONIT TESNIT, D.O.O.**

Cesta komandanta Staneta 38, 1215
Medvode, Slovenia
Phone: +386 (0)1 582 33 00
E-mail: info@donit.eu

China**SUZHOU DONIT SEALING
MATERIALS**

Import and Export Co., Ltd.
No. 8 Suzhou Avenue West,
Bank of China Building, Room 1904,
SIP, 215021, P.R. China
Phone: +86 (0)512 659 535 29
E-mail: sales.suzhou@donit.eu

India**DONIT TESNIT INDIA**

C-406, Mantri Lavendula Mulshi
Road,
Bavdan Khurd, Pune - 411 021, India
Phone: +91 20 6520 7558
E-mail: sales.india@donit.eu

Middle East**DONIT TESNIT MIDDLE EAST**

E-mail: sales.middleeast@donit.eu

North America**DONIT TESNIT NORTH AMERICA**

E-mail: sales.northamerica@donit.eu

Latin America**DONIT TESNIT LATIN AMERICA**

E-mail: sales.latinamerica@donit.eu

Slovenia**DONIT TESNIT, D.O.O.**

Donit Industrial Sealing Solutions
Paradiž 4, 8210 Trebnje, Slovenia
Phone: +386 (0)8 205 50 44
E-mail: salesgaskets@donit.eu

Belgium**DISS-EUROPE BVBA**

Donit Industrial Sealing Solutions
Toekomstlaan 34,
2200 Herentals, Belgium
Phone: +32 (0)14 302 100
E-mail: sales@disseurope.be